

Chinese stainless steel grades in approximate comparison with countries of Germany and England.

NO.	China GB	Germany DIN	England BS
1	00Cr18Ni 14Mo2Cu2		
2	0Cr19Ni 13Mo3	X5CrNi Mo17-13	317S16
3	1Cr18Ni 12Mo3Ti		320S31
4	0Cr18Ni 12Mo3Ti	X6CrNi MoTi 17-12-2	320S17
5	00Cr19Ni 13Mo3(00Cr17Ni 14Mo3)	X2CrNi Mo18-16-4	317S12
6	0Cr18Ni 16Mo5		
7	1Cr18Ni 9Ti	X12CrNi Ti 18-9	321S20
8	0Cr18Ni 11Ti (0Cr18Ni 9Ti)	X6CrNi Ti 18-10	321S12 321S31
9	0Cr18Ni 11Nb	X6CrNi Nb18-10	347S17 347S31
10	0Cr18Ni 9Cu3	X3CrNi Cu18-9	
11	0Cr18Ni 13Si 4		
奥氏体-铁素体型不锈钢			
12	0Cr26Ni 25Mo2	X8CrNi Mo27-5	
13	1Cr18Ni 11Si 4AlTi		
14	00Cr18Ni 15Mo3Si 2		
铁素体型不锈钢			
15	0Cr13Al	X6CrAl 13	405S17
16	00Cr12		
17	1Cr17	X6Cr17	430S15
18	YCr17	X12CrMoS17	
19	1Cr17Mo	X6CrMo17	434S17
20	00Cr30Mo2		
21	00Cr27Mo	X1CrMo26-1	
马氏体型不锈钢			
22	1Cr12		403S17
23	0Cr13Al	X6Cr13	
24	1Cr13	X10Cr13	410S21
25	1Cr13Mo	X15Cr13	420S29
26	Y1Cr13	X12CrS13	416S21
27	2Cr13	X20Cr13	420S37
28	3Cr13	X30Cr13	420S45
29	4Cr13	X38Cr13	
30	Y3Cr13		
31	1Cr17Ni 2	X20CrNi 17-2	431S29
32	7Cr17		
33	8Cr17		
34	11Cr17(9Cr18)		
35	Y11Cr17		

沉淀硬化型不锈钢			
36	0Cr17Ni 14Cu4Nb	X5CrNi i CuNb17-4	
37	0Cr17Ni A1	X7CrNi Al 17-7	
38	0Cr15Ni 7Mo2Al		
补充			
39		X38Cr13	
40		X46Cr13	420S45
41		X105CrMo17	
42		X5CrNi 13-4	425C11
43		X2CrNi Mo17-13-2	316S11
44		X6CrTi 17	
45		X8CrNb17	
46		X5CrNi Nb18-10	347S17 347S18
47		X10CrNi MoTi 18-12	320S33
48		X6CrNi MoNb17-12-2	318S17